

**ATTAR TEST REPORT NUMBER: 12/5922**

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards. Accredited for compliance with ISO/IEC 17025. Accreditation Number: 2735

26 April 2012

Total Pages: 1**DRY SLIP RESISTANCE**

Job No: M12/5922

Prepared for:	PM Timber Unit 19, 323 – 325 Woodpark Road SMITHFIELD NSW 2164		
Attention:	Mr Peter Chan		
Test Site:	ATTAR, Unit 1, 64 Bridge Road, Keysborough.		
Test Date:	26 April 2012		
Test Specimens, Size and Quantity:	Timbernate Diamond Life Veneer, 140x900 mm, 3 off supplied.		
Sampling and Direction of Test:	Sampling conducted by client. Test direction parallel with grain pattern.		
Test Personnel:	Steven Potts		
Preparation:	Washed with water and pH neutral detergent, rinsed then dried.		
Fixed/Unfixed:	Unfixed		
Air Temperature:	19°C		
Test Equipment:	Tortus Floor Friction Tester; Tortus Model Mk III (with integral printer), Serial No: 318.		
Test Standard:	AS/NZS 4586: 2004 Slip resistance classification of new pedestrian surface materials – Appendix B.		
Slider Rubber:	Slider 96 (Four S) Batch No. 40		
Classification Criteria:	Refer Appendix 1 – Classification Criteria, attached.		
Dynamic Coefficient of Friction	Run 1	Run 2	Mean Rounded to 0.05
	0.72	0.72	0.70
Classification:	F		

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip-resistance be checked.

NOTE: Any specimens supplied will be disposed of in two (2) months time, unless otherwise instructed.

ATTAR

Steven Potts
Slip & Engineering Technician
Approved Signatory

This report may not be reproduced except in its entirety.

Page 1 of 1

APPENDIX 1

**CLASSIFICATION CRITERIA – AS/NZS 4586 - 2004****Compliance****TABLE 1
TEST AND CLASSIFICATIONS COMBINATIONS**

Test conditions	Test method	Classification table to be used
Wet pendulum	Appendix A	Table 2
Wet pendulum and dry floor friction	Appendices A and B	Tables 2 and 3
Dry floor friction	Appendix B	Table 3*

*Samples tested under dry conditions only are assumed to have a default wet classification of Z and shall be reported as classification ZF or ZG.

**TABLE 2
CLASSIFICATION OF PEDESTRIAN SURFACE MATERIALS
ACCORDING TO THE WET PENDULUM TEST**

Class	Pendulum* mean BPN	
	Slider 96 (Four S rubber)	Slider 55 (TRL rubber)
V	>54	>44
W	45-54	40-44
X	35-44	-
Y	25-34	-
Z	<25	-

*While either of these test methods may be used, the test report shall specify which method was used.

NOTE: It is expected that these surfaces will have greater slip resistance when dry.

**TABLE 3
CLASSIFICATION OF PEDESTRIAN SURFACE MATERIALS
ACCORDING TO THE DRY FLOOR FRICTION TEST**

Classification	Floor friction tester mean value
F	≥0.4
G	<0.4

Means of demonstrating compliance

Pedestrian surfaces that are classified in accordance with Table 2 and, where appropriate, Table 3 shall meet the following criteria:

- (a) The mean test results shall be as follows:
 - (i) For the classifications in Table 2, the mean of the test results shall be within the relevant criteria set out in the Table, and each individual result shall be equal to or above the lower limit for the classification or, if below the classification, within the mean of the result minus 20%. If either of these criteria is not met, the lot shall be considered to be a lower classification.
 - (ii) For Classification F in Table 3, the mean of the test results shall be equal to or greater than 0.4 and each individual result shall be equal to or greater than 0.35. If either of these criteria is not met, the lot shall be considered to be Classification G.
- (b) The classification in accordance with Table 2 or Table 3 shall be determined by –
 - (i) selecting and testing at least five specimens at random as defined in Appendices A and B; or
 - (ii) carrying out continuous testing and process control in accordance with AS 3942.
- (c) When testing individual lots, if a particular test fails to produce the expected classification it shall be permissible to:-
 - (i) disregard the first sample, re-sample a minimum of 10 specimens from the whole lot, retest and apply the criteria to the new sample; or
 - (ii) subdivide the lot into smaller lots of different quality, re-sample, retest and reclassify each of the smaller lots.