

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

**Client :** Eco Flooring Systems Pty Ltd  
6G/33 Hope Street  
Melrose Park NSW 2114

**Test Number :** 16-001230  
**Issue Date :** 04/04/2016  
**Print Date :** 18/05/2016

**Sample Description** Clients Ref : "Ornato Looselay Vinyl Flooring"  
Vinyl Flooring  
End Use : flooring  
Nominal Composition : DuraCoat, 0.5mm wear layer,decor layer, recycled vinyl, fibreglass core, sound barrier backing  
Nominal Mass per Unit Area/Density : Approx: 820g/m2  
Nominal Thickness : 5mm

AS/ISO 9239.1-2003

### Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 10/03/2016

Date Tested 04/04/2016

CHF Value	1	2	3	Mean
Length	8.2	8.6	8.0	8.3 kW/m <sup>2</sup>
Width	8.8	-	-	- kW/m <sup>2</sup>

Smoke Value	1	2	3	Mean
Length	233	240	262	242 %min
Width	234	-	-	- %min

Melting Yes

Blistering Yes

58773

10865

Page 1 of 2

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025

- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

Accreditation No. 983

Accreditation No. 985

Accreditation No. 1556

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by



  
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)  
MANAGING DIRECTOR